

W186 N11687 MORSE DRIVE GERMANTOWN, WI 53022
262-502-6610 FAX 262-502-4743

DESCRIPTION:

Cynergy CA7008 is a medium viscosity ethyl cyanoacrylate adhesive. It sets extremely quickly, typically in several seconds on most substrates. It is specifically formulated for wire tacking and bonding plastic parts, but it can be used with a variety of substrates including rubber, wood, and metal. This product meets Military specification MLLA 46050 Type II Class II.

Common substrates

- | | | |
|---------------|-----------------|-------------------|
| ■ Acrylic | ■ Polycarbonate | ■ Polyimide |
| ■ PVC | ■ PEEK | ■ PETG |
| ■ Polysulfone | ■ Wood | ■ Latex |
| ■ Steel | ■ Aluminum | ■ Zinc Dichromate |

Set Times:

At standard indoor temperature and humidity, surface moisture on the substrates initiates the curing process. Handle strength is developed in a short time but curing continues for at least 24 hours before full chemical/solvent resistance is developed. The rate of cure will depend on substrate used.

<i>Substrate</i>	<i>Set Time (seconds)</i>	<i>Substrate</i>	<i>Set Time (seconds)</i>
Plastics	3-6	Leathers	7-17
Rubbers	<3	Metals	9-12
Wood	1-6	Ceramics	14-20

Typical Lap Shear:

my note ASTM D1002 N/mm X 145 = psi

<i>Substrate</i>	<i>Lap Shear (psi)</i>	<i>Substrate</i>	<i>Lap Shear (psi)</i>
Grit Blasted Steel	> 3190	Etch Aluminum	> 2610
Rubber	> 2900	Wood	> 3625
Polycarbonate	> 2000	ABS	> 1740

PHYSICAL PROPERTIES:

All properties given are at 25°C unless otherwise noted.

<u>PROPERTY:</u>	<u>VALUE:</u>	<u>TEST METHOD:</u>
Color	Clear	
Viscosity	700 cps	
Nominal Gap fill	0.35 mm	

W186 N11687 MORSE DRIVE GERMANTOWN, WI 53022
262-502-6610 FAX 262-502-4743

<u>PROPERTY:</u>	<u>VALUE:</u>	<u>TEST METHOD:</u>
Specific Gravity	1.05	
Glass Transition Temp (by DSC)	120 °C	ASTM E228
Melting Point	160-170 °C	
Tensile Strength	2900 - 4060 psi	
Thermal Conductivity	0.1 W/m ² K	ASTM C177
Coefficient of Thermal Expansion	100 ppm/°C	ASTM D696
Dielectric Constant	2.3	ASTM D150
Dielectric Strength	635 v/mil	ASTM D149
Volume Resistivity	1x10 ¹⁶ Ohm.cm	ASTM D257
Temperature Range **	-60 to 80°C	

INSTRUCTIONS:

1. Bring to room temperature prior to use if stored refrigerated. Surfaces should be clean and dry and free of grease or debris. A light abrasion is recommended if possible.
2. If using an accelerator, apply to one surface only. Apply a thin film of adhesive to the other side and assemble immediately. Do not disturb or re-align joint until parts are set.
3. When bonding "O" rings, cut a fresh surface onto each end of the rubber to gain the best possible strength.

STORAGE:

Shelf life is one year at room temperature (77°F / 25°C). Refrigerated storage at 40°F is recommended to maximize shelf life. When stored in a refrigerator, allow the adhesive to gradually warm to room temperature prior to use. Avoid heat, direct sunlight and high moisture areas when storing. Avoid contaminating open containers. Do not return unused adhesive to original container. DO NOT refrigerate open containers.